



Specifications:

<u>Property</u>	<u>Units</u>	<u>Typical Value</u>	<u>Test Method</u>
Durometer, 15 sec	Shore A	58 (±3)	ASTM D2240
Density	g/cm ³	1.17 (±0.03)	ASTM D792
Tensile Strength	PSI	1,710	ASTM D412
Aged 7 days, 136°C	% of Original	119	UL Standard
Oil Aged 7 days, 60°C	% of Original	112	UL Standard
Elongation	%	350	ASTM D412
Aged 7 days, 136°C	% of Original	85	UL Standard
Oil Aged 7 days, 60°C	% of Original	86	UL Standard
100% Modulus	PSI	600	ASTM D412
Deformation, 1 hr. 150°C	%	63	UL Standard
Brittle Point	°C	-53	ASTM D746
Oxygen Index	%	26.5	ASTM D2863